

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 13/14	A1	(11) International Publication Number: WO 99/01214 (43) International Publication Date: 14 January 1999 (14.01.99)
(21) International Application Number: PCT/NL98/00377 (22) International Filing Date: 1 July 1998 (01.07.98) (30) Priority Data: 1006444 1 July 1997 (01.07.97) NL (71) Applicant (for all designated States except US): INSTI- TUUT VOOR AGROTECHNOLOGISCH ONDERZOEK (ATO-DLO) [NL/NL]; P.O. Box 17, NL-6700 AA Wageningen (NL). (72) Inventors; and (75) Inventors/Applicants (for US only): VAN SOEST, Jeroen, Jo- hannes, Gerardus [NL/NL]; Broekemalaan 2, NL-6703 GL Wageningen (NL). VAN SCHIJNDEL, Renée, Josie, Gide [NL/NL]; Sterappel 33, NL-4191 DM Geldermalsen (NL). GOTLIEB, Kornelis, Fester [NL/NL]; Wildervankstraat 12, NL-9643 LC Wildervank (NL). (74) Agent: DE BRUIJN, Leendert, C.; Nederlandsch Octrooibu- reau, Scheveningseweg 82, P.O. Box 29720, NL-2502 LS The Hague (NL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: ENCAPSULATION OF ACTIVE INGREDIENTS		
(57) Abstract Microspheres having a particle size of 50 nm to 1 nm and a polydispersity of less than 40 %, consisting of a chemically cross-linked starch shell containing an active ingredient, are obtained by preparing an oil-in-water emulsion of the active ingredient in a hydrophobic phase and starch or a dispersion of a solid active ingredient and starch in water, incorporating the oil-in-water emulsion or solid dispersion in an outer hydrophobic phase, particles of the oil-in-water emulsion or solid dispersion being formed in the outer hydrophobic phase, cross-linking the starch or derivative thereof and removing the outer hydrophobic phase if desired.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Encapsulation of active ingredients

The invention relates to a process for the preparation of microparticles which contain an active ingredient in a starch shell.

A process of this type is disclosed in WO 89/03674. According to this known
5 process, microspheres are prepared by suspending an active ingredient, such as paramagnetic particles, in a starch solution, cross-linking the starch with a phosphate and then emulsifying the starch, before or after cross-linking, in a hydrophobic medium.

WO 93/02712 discloses a process for the preparation of microspheres according to which an oil-in-water emulsion of a soluble starch fraction and, for example,
10 dichloromethane is prepared, after which a dehydrating agent, such as an alcohol, is added. The particles are fixed by retrogradation of the starch, which therefore must have a high amylose content.

WO 94/07597 discloses a process for encapsulating an oil phase in a polymeric material that can be cross-linked. The polymeric material is a water-soluble polymer
15 such as polyvinyl alcohol dissolved in water (e.g. at 10%). Acrylamide polymers, soluble cellulose, starch and other polysaccharide derivatives are mentioned as alternatives, but the document does not contain any guidance or illustration on the utility of such soluble polysaccharides. Moreover, solutions put limitations e.g. to the molecular weight and concentration of the polymer.

20 A process has now been found which leads to convenient particles in which an active ingredient is encapsulated, which active ingredient is released only under specific chosen conditions or after a relatively long period. The process is characterised by the features in the appended claims.

A fine distribution of the active ingredient can be a dispersion of a solid water-
25 insoluble active ingredient or an emulsion of a hydrophobic active ingredient (optionally dissolved in a hydrophobic phase such as an oil). The fine distribution (dispersion or emulsion) is a distribution in an aqueous dispersion of starch or derivative thereof. Examples of water-insoluble solid active ingredients comprise pigments such as titanium dioxide or zinc oxide, paramagnetic materials such as magnetite, nickel or cobalt,
30 fluorescent materials and the like. The particles size of the solid active ingredient can be in the range of e.g. 10 nm to 50 μ m. In the further specification, the distribution of the

active ingredient is illustrated with reference to the oil-in water emulsion; however, the same applies to the solid-in-water dispersion by substituting the oil by the solid active ingredient.

An important constituent of the microparticles is starch, which has the advantage of being able to encase a multiplicity of active ingredients and of being biodegradable. Suitable starches are native starch and fractions and derivatives thereof. Preferably, the starch is granular starch, which can be native or modified native starch and is not water-soluble.

Granular starch is starch having a granular shape similar to the shapes which occur in native starch. Granular starch can have various shapes and sizes (usually in the range of 0.5-175 microns) characteristic of its native source. In most cases, birefringence is seen with polarised light microscopy. Granular starch is usually semi-crystalline. It is not soluble in cold water without the use of chemicals. Granular starch is swellable to a limited extent only. The water uptake is limited (less than 5 times its own weight). As granular starch is also considered chemically or physically modified starch of which most of the original shape and size is maintained during modification. Suitable derivatives are oxidised starch (carboxy starch, dialdehyde starch), carboxyalkylated starch, sulphated or phosphated starch, cationic starch and the like. These modified granular starches usually show still birefringence, but the crystalline nature can be significantly reduced. The modified granular starches do not form gels in cold water without the addition of chemicals. All granular starches show a characteristic gelatinisation endotherm with DSC or an increase in viscosity during heating in water.

The use of granular starches has some advantages over the use of soluble starches. A higher starch concentration can be used, or starch with a higher molecular weight. Thus, a shell can be prepared that has a higher network density, which may be advantageous for the release properties. Another advantage of using granular starch is that various types of starch can be used, such as high-amylose starch, which cannot be used in solution because of rapid retrogradation. Also, the degree of gelatinisation can be controlled through temperature control or adjustment of the amount of alkaline solution added; the degree of gelatinisation allows for adjustment of the network structure; if desired, particles with residual granular structure can be obtained. When the starch is not completely gelatinised, remainders of granular structures will be present. Such granular

structures can be observed using (polarised) light microscopy or scanning electron microscopy. Via this route, the swelling behaviour and the release properties of the particles can be adjusted. For example, the release in the gastrointestinal tract may be spread or delayed as a result of the presence of granular structures.

5 The starch concentration in the aqueous phase before formation of a fine distribution can be e.g. from 5 to 50 % by weight, preferably from 15 to 40 % by weight, with respect to the water volume. The initial molecular weight of the starch is advantageously above 200,000, especially above 500,000.

10 It is possible to use a mixture of various types of starch. For instance, partially soluble starch can be added to native starch. Suitable starch fractions are, for example, starch enriched in amylose or specifically in amylopectin. In order to optimise the properties of the particles an auxiliary substance can be added to the starch suspension that modifies the viscosity of the suspension, at a level of 0 to 75 wt.% of the total amount of carbohydrates, preferably 0 to 50 wt.%, more preferably 1 to 25 wt%, in
15 particular 2 to 10 wt.%. This auxiliary substance can be a water-soluble carbohydrate, such as cold water soluble starch, modified starch, cellulosic derivatives such as carboxymethyl cellulose, alginates, pectines and the like.

 The oil-in-water emulsion can be prepared in a manner known per se by adding an oil or another hydrophobic substance to the aqueous solution or dispersion of starch.
20 Suitable oils or hydrophobic substances are all water-immiscible liquids, such as hydrocarbons (alkanes, cycloalkanes), ethers, esters, halogenated hydrocarbons and oils. If the active ingredient is also hydrophobic, it can advantageously be added via the oil. The emulsion is formed by adding the hydrophobic phase to the suspension of starch in water. Preferably a soap or another surfactant, which promotes the formation of an oil-
25 in-water emulsion, is added to the aqueous phase before the hydrophobic phase is added. The amount of surfactant is preferably between 0.25 and 5 wt.% with respect to the water volume. Following the addition, a stable emulsion is formed by employing adequate mechanical forces. In this context stable is understood to be stable for the duration of the process. Equipment which can be used for this process is, for example, a top stirrer, an
30 Ultra-Turrax, a homogeniser or any other suitable emulsion-forming equipment. The dispersion of solid active ingredient can be prepared in the same manner.

 After a stable oil-in-water emulsion has been obtained, a particulate material is

prepared therefrom by dispersing the emulsion in a hydrophobic phase. The hydrophobic phase can be formed by a water-immiscible solvent, such as an alkane, cycloalkane, ether, ester, halogenated hydrocarbon and the like, or an oil. An oil-in-water-in-oil (o/w/o) emulsion is thus obtained. The conditions for emulsion formation can be the same as those for the formation of the first o/w emulsion. During this stage it is also possible to add, to the second hydrophobic phase, a soap or another surfactant which promotes the formation of a water-in-oil emulsion. Similarly a solid-in-water-in-oil emulsion is obtained from the solid dispersion and the hydrophobic phase.

Cross-linking takes place after the emulsion or dispersion has been dispersed in a hydrophobic substance. When granular starch is used, the starch is simultaneously completely or partially gelatinised and cross-linked after emulsification. During preparation of the oil-in-water-in-oil (or solid-in-water-in-oil) emulsion, the integrity of the granular starch or cold water insoluble starch is kept intact. After the formation of the emulsion, preferably during crosslinking, the granular integrity can be changed by gelatinisation as a result of an increase in temperature or an addition of alkaline or acid or other chemicals. Preferably the granular shape is at least partially maintained, so that residual granules or remnants or partially gelatinised starch are present in the particles.

Cross-linking can be effected by means of a cross-linking agent, which preferably is added beforehand to the starch solution/dispersion. Cross-linking can be initiated at the desired point in time, preferably after the formation of particles in the suspension or emulsion has taken place, by adding a catalyst, for example a base, a salt or an acid, depending on the type of cross-linking reaction. Cross-linking can also optionally be initiated by raising the temperature. The cross-linking agent used can be a conventional cross-linking agent, such as epichlorohydrin, phosphoryl chloride or an anhydride of a dibasic or polybasic carboxylic acid. However, the use of a phosphate, such as trisodium trimetaphosphate, as cross-linking agent is particularly preferred. In these cases the catalyst can be a base, such as sodium hydroxide. Per anhydroglucose unit, 20 to 500 mmol cross-linking agent per mol anhydroglucose units is preferably used. The quantity to be used is partly dependent on the active ingredient and on the desired rate of release.

In the case of dialdehyde starch, the cross-linking agent can, for example, be a diamine, such as urea, tetramethylenediamine or hexamethylenediamine, it being possible

to use an acid as catalyst. In the case of, for example, carboxymethyl starch or dicarboxy starch, a diamine or a diol can also be used for cross-linking. In this case, however, cross-linking can also, and advantageously, be achieved by internal esterification, which can be catalysed by a polyvalent metal ion, such as calcium, magnesium, aluminium, zinc or iron, preferably calcium. Another possible starting material is cationic (aminoalkyl) starch, which can be cross-linked in situ using a dicarboxylic acid or a dialdehyde.

The particle size of the microparticles according to the invention is preferably between 50 nm and 1 mm. The particles are usually spherical and are virtually monodisperse. The polydispersity is at most 40 %, in particular less than 30 %. Active ingredients that can be used are, for example, perfumes, flavours, colorants, medicaments (for example hormones, anti-inflammatory agents, insulin, chemotherapeutic agents), vaccines, vitamins (for example A and D), nutrients, such as polyunsaturated fats and fatty acids (fish oil), proteins and peptides, fertilisers, pesticides (for example atachlor), reagents or catalysts for chemical reactions, coatings, paints, ink, diagnostic agents, etc.

The degree of loading of the microparticles is partly dependent on the hydrophobic phase of the first (o/w) emulsion. If the active ingredient itself is the hydrophobic substance, that is to say, without a hydrophobic excipient, the loading is in general between 0 and 60 % by weight of the total weight of the starch (solids), in particular between 5 and 25 % by weight. If the active ingredient is dissolved in the hydrophobic phase, the loading is between 0 and 20 % by weight, in particular between 2 and 10 % by weight, depending on the solubility.

The active ingredient can be released in a target environment by chemical, enzymatic or physical modification or degradation of the starch shell. For instance, the active ingredient can be released in the digestive tract under the influence of the different conditions (pH, amylases); the sensitivity to a particular pH or to a particular enzyme can optionally be increased or reduced by modification of the starch used as starting material. In detergents, for example, release can be promoted by raising the temperature or by pH or enzyme effects. In land for cultivation or potting compost, release can be effected by hydrolysis or the action of salts. In reaction mixtures release can also be effected, for example, under the influence of electric current or a change in pH.

The microparticles can be used in detergents, fertilisers, foods, flavourings, pharmaceutical agents, tissues, cosmetics, soil improvers, pesticides (fungicides,

bactericides, insecticides, acaricides, nematocides, and the like), coatings, paints, ink, organic reactants (hydrogen peroxide), catalysis and diagnostic agents. The quantities to be used are the quantities customary for the application concerned.

Example 1

5 A suspension of 20 g PN (native potato starch) in 200 ml water in which 5 ml Tween 80 had been dissolved was prepared. 2 g TSTP was then dissolved in this suspension. 20 ml salad oil was then added and an emulsion was formed with the aid of an Ultra-Turrax. The o/w emulsion was then emulsified in a second hydrophobic phase, namely 400 ml peanut oil. A top stirrer at a stirrer speed of 800 rpm was used for this
10 purpose. A solution of 5 g NaOH in 50 ml water was added to the solution with stirring, in order to initiate cross-linking. After 4 hours the emulsion was broken by adding acetic acid. The starch particles collected in the water/acetic acid phase. After separation, the particles were washed a few times with demineralised water and this was followed by washing with ethanol and air-drying.

Example 2

15 10 g Flocgel LV-W was dissolved in 200 g water in which 5 ml Tween-80 had been dissolved. 10 g PN and 2 g TSTP were added to the solution. 20 ml salad oil was added to the slurry, after which an emulsion was formed with the aid of an Ultra-Turrax. The emulsion was added to 400 ml peanut oil and the secondary emulsion was formed
20 using a top stirrer. A solution of 5 g NaOH in 50 ml water was added, whilst stirring, to initiate cross-linking. After 18 hours the emulsion was broken with acetic acid. The starch particles collected in the water/acetic acid phase. After separation, the particles were washed a few times with demineralised water and this was followed by washing with ethanol and air-drying.

Example 3

25 Twenty grams of PN were added to 200 ml water in which 5 g Tween 80 was dissolved. Four g TSTP was dissolved in this suspension, followed by the addition of 20 g of salad oil. An emulsion was formed with the aid of an Ultra-Turrax. The o/w emulsion was then emulsified in a second hydrophobic phase, namely 400 ml of paraffin
30 oil. A top stirrer at a stirrer speed of 1400 rpm was used for this purpose. A solution of 1.2 g NaOH in 10 ml water was subsequently added to the emulsion with stirring, in order to initiate partial gelatinisation and cross-linking. The concentration was chosen

such that complete gelatinisation is prevented. After 4 hours the emulsion was broken by addition of acetic acid. The starch particles collected in the water/acetic acid phase. After separation, the particles were washed with demineralised water and kept as a dispersion. Light microscopy showed particles containing oil, in which residual granular structures were clearly visible.

Example 4

Fifteen grams of PN were added to 100 ml water in which 2.5 g Tween 80 was dissolved. Four g TSTP was dissolved in this suspension, followed by the addition of 20 g of salad oil. An emulsion was formed with the aid of an Ultra-Turrax. The o/w emulsion was then emulsified in a second hydrophobic phase, namely 200 ml of paraffin oil. A top stirrer at a speed of 600 rpm was used for this purpose. A solution of 0.65 g NaOH in 10 ml water was subsequently added to the emulsion with stirring, in order to initiate partial gelatinisation and cross-linking. After 30 minutes, the stirrer speed was increased to 1000 rpm. After 4 hours the emulsion was broken by addition of acetic acid. The starch particles collected in the water/acetic acid phase. After separation, the particles were washed with demineralised water and kept as a dispersion. Light microscopy showed essentially monodisperse particles with a size of 25 μm containing droplets of oil.

Claims

1. A process for preparing microparticles which contain an active ingredient in a starch shell, characterised by preparing a fine distribution of the active ingredient and starch or a derivative thereof in water, taking up said distribution in a hydrophobic phase, particles of the distribution being formed in the hydrophobic phase, cross-linking the starch or derivative thereof and, if desired, removing the hydrophobic phase.
2. A process according to Claim 1, wherein said fine distribution of the active ingredient and starch in water is an oil-in-water emulsion.
3. A process according to Claim 1 or 2, wherein the starch or its derivative comprises at least 25% granular starch.
4. A process according to any one of Claims 1-3, wherein a water-soluble carbohydrate is added to the starch before preparing said oil-in-water emulsion in an amount of 0-50%, preferably 1-25%, by weight with respect to the total of said starch and said water-soluble carbohydrate.
5. A process according to any one of Claims 1-4, wherein a cross-linking agent is added to the starch before the preparation of the oil-in-water emulsion.
6. A process according to Claim 5, wherein the cross-linking agent is a diamine, a dialdehyde, an epoxide or, preferably, a trimetaphosphate.
7. A process according to Claim 5 or 6, wherein cross-linking is started by adding a cross-linking catalyst.
8. A process according to any one of Claims 1-4, wherein the starch derivative is a carboxyalkyl starch and cross-linking is carried out by adding a polyvalent metal ion.
9. A process according to any one of Claims 1-8, wherein said starch has an average molecular weight of more than 200,000.
10. A process according to any one of Claims 1-9, wherein a surfactant is added to the starch.

11. A process according to any one of Claims 1-10, wherein the active ingredient is a medicament, fat component, peptide, pesticide, organic reactant, paramagnetic substance, catalyst, colorant, perfume, flavour or nutrient.
12. Microspheres having a particle size of 50 nm to 1 mm and a polydispersity of less than 40 %, consisting of a chemically cross-linked starch shell containing a hydrophobic phase containing active ingredient, the microspheres being obtainable using the process according to one of Claims 1-11.
13. Microspheres according to Claim 12, in which the starch is partially gelatinised and granular structures are still present in the shell.
14. Use of microparticles according to Claim 12 or 13 or obtained according to any one of Claims 1-11, in detergents, cosmetics, foods, medicaments, coatings, paint, ink, tissues, organic synthesis, diagnostic agents or in agriculture.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/NL 98/00377

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 B01J13/14

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 07597 A (ALLIED COLLOIDS) 14 April 1994 cited in the application see page 7, line 19 - page 9, line 18; claims 1-10 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

" Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

29 October 1998

Date of mailing of the international search report

06/11/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fouquier, J-P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/NL 98/00377

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9407597 A	14-04-1994	AU 4832293 A	26-04-1994

THIS PAGE BLANK (USPTO)